



Rainbow Interior Boiler Composition

Rainbow interior boiler composition is developed for all interior boiler drums, pipes and steam turbine casings.

Specification:

Composition

Application

Covering

No. of Coats

Dry time

Film Thickness

Flash point

Pack

Thinner

Colour

Finish

Surface Preparation

Graphite and Gilsonite

Brush & Spray

8-10 Sq. Meter / Ltr.

2 Coats at interval of 8 hours

S.D 3-4 Hours

25-30 Micron per coat

73°C

3.64 & 14.56 Liters.

Mineral turpentine

Black

Glossy

Remove all base mills scale & rust by sand blasting, in Case

is not passable use mechanical tools or wire brushing.

Note: The above Information is given in good faith, but without any warranty.

Rainbow Paint Industries

Quality & Standard Caint Manufacturer

Email: karachi@rainbow-paints.com, Web: www.rainbow-paints.com

Regional Office:

House No. 5 Lane No. 1, Scheme No. 02, PF Chowk Tipu Road, Chaklala Rawalpindi

Ph: 051-5590971, 051-5591436, 051-5961401